

TEST REPORT

Report Ref.	LEI19041732A Original		
Date Received	08/04/2019	Date Issued	15/04/2019

Company Name & Address	Camira Fabrics Limited Meltham Mills Meltham, HD9 4AY
Contact Name	Greta Ziaugraite

Order Number	83A03522
Sample Description	Velocity
Ref / Style Number	Hvel00f00
Colour	Polar
Quality	Velocity
Batch Number	368500(08020)
End Use	Contract Upholstery
Quoted Fibre Composition	100% Polyester
Retailer	General

Test	Method	Sample	Result
Martindale Abrasion Resistance	BS EN ISO 12947-2: 2016		Not Applicable

Tests marked (^) in this report have been performed by an approved 3rd party laboratory.
Tests marked (*) in this report are not included in our UKAS scope of accreditation.



Heather Fletcher
(Jobsheet Team Leader)

Martindale Abrasion Resistance BS EN ISO 12947-2: 2016
Conditioning Parameters: 20°C±2°C & 65% rH±4% rH

	Results	Requirement
Shade change @ 3000	4-5	
	4-5	
	4-5	
	Abrasion Resistance*	
Specimen 1	90,000 Revs	
Specimen 2	90,000 Revs	
Specimen 3	90,000 Revs	
Overall result**	90,000 Revs	
Test Information		
Test load:	12 kPa	
Fabric type	Knitted	
Breakdown criteria	One thread completely broken	
Inspection interval	Every 10,000 Revs	
Foam used	Yes	
Preparatory treatment	No	
*The abrasion resistance result is the last inspection point at which no breakdown was observed.		
**The overall result is the lowest individual test result of all the test specimens tested.		

Overall Test Result: Not Applicable
Uncertainty: ±17%

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or willful misconduct.

The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor of $k = 2$, providing a level of confidence of approximately 95 %. Any Pass/Fail statements do not take into account the Measurement of Uncertainty. The Uncertainty budgets are stated for each Test method, these are for reference, and should be considered when results are close to Specification Limits / Requirements.